

# QB-9511

Alkyd Graphite Paint  
Black



## Product Data Sheet

### **PRODUCT DESCRIPTION:**

EZ-SLIDE® is a graphite H<sub>2</sub>O®-based lubricating paint that bonds quickly to any clean metal, wood, concrete and most plastic surfaces.

### **TYPICAL USES:**

EZ-SLIDE® H<sub>2</sub>O®-based lubricating graphite paint can be used on farm equipment, industrial or home applications such as gravity boxes, corn picker heads, bean combines, mowers, truck and wagon beds, dump bins, snowplow blades, etc.

### **BASES & COLORS:**

QB-9511 H<sub>2</sub>O®- Graphite Paint  
Black

### **PHYSICAL PROPERTIES:**

PRODUCT NUMBER:	QB-9511
GENERAL TYPE:	H <sub>2</sub> O®- Graphite Paint
COLOR:	Black
GLOSS:	1.0 @ 60°
SOLIDS BY WEIGHT:	40.15%
SOLIDS BY VOLUME:	29.63%
THEORETICAL COVERAGE @ 1 MIL DFT:	475.31 Sq. Ft. /Gal
RECOMMENDED DFT:	2 – 2.5mils DFT
VISCOSITY @ 78°F:	88-92 KU
WEIGHT PER GALLON:	8.2 lbs.
FLASH POINT:	200°G
VOC:	347.54 g/L

### **SURFACE PREPARATION:**

The surface to be painted must be clean and dry. Remove all dirt, grease or loose scaling paint by wire brushing, scraping or sanding. Sand all glossy surfaces with sandpaper for better adhesion. Any rusty metal should be cleaned, and the rust that is present removed. To properly clean new metal surfaces, remove mil film by degreasing or etching as needed. Premature peeling is caused by improper surface preparation. Do not use oil or grease after applying EZ-SLIDE® as it will tend to loosen the bond.

### **APPLICATION:**

Apply with a clean brush or sprayer. If thinning is necessary use a small amount of paint thinner. Allow to dry for at least 45 minutes at 70° before applying a second coat to insure a good film base.

### **ENVIRONMENTAL VARIABLES:**

Apply only when surface and air temperatures are between 50° and 90°F. Avoid painting late in the day when dew and condensation are likely to form or when rain is threatening. Avoid painting on hot days in direct sunlight. Cool, wet, humid or over-applied coatings can greatly decrease a thorough cure and interfere with proper film formation. Always allow applied coat to dry before applying subsequent coats.

### **Dry-Times:**

Drying time for this product will be approximately 45minutes at 70° until recoat. Allow to dry overnight before use.

### **CLEAN-UP:**

Clean up all tools and equipment with water.



# QB-9511

Alkyd Graphite Paint  
Black



## Product Data Sheet

---

### **CAUTIONS:**

For exterior use only,  
Do not take internally,  
Use with adequate ventilation,  
KEEP OUT OF REACH OF CHILDREN

\*WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the national Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

For additional Product Information or Safety Data Sheets, please call 800-677-2468, 8:00-5:00 CST Mon.-Fri.

### **Limited Warranty**

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since Van Sickle Paint does not control the application of its products, or the condition of the surfaces to which they are applied, Van Sickle Paint's liability will under no circumstances exceed replacement of the product.

