

1372

Exterior Oil Barn & Building Semi-Gloss White Oil



Product Data Sheet

PRODUCT DESCRIPTION:

Tallman Ag Specialty Barn and Out Oil Based Barn Paint is our Premium quality, <150 g/L VOC, linseed oil finish, custom designed for use on farm and ranch buildings, other utility buildings and fences. This product gives a uniform finish that will protect and beautify the surface for years to come. It is formulated for high hiding, excellent color retention, and outstanding durability.

TYPICAL USES:

For use on all properly prepared surfaces of wood. Do Not Apply Tallman's Linseed Oil-Based Paints over steel, iron, metal, galvanized metal, coil-coated metal, aluminum, masonry, or asbestos.

BASES & COLORS:

Semi Gloss White

PHYSICAL PROPERTIES:

PRODUCT NUMBER:	1372
GENERAL TYPE:	Oil base exterior oil
COLOR:	White
GLOSS:	50-60 @ 60°
SOLIDS BY WEIGHT:	61%
SOLIDS BY VOLUME:	44.9%
THEORETICAL COVERAGE @ 1 MIL DFT:	720 SF./Gal
RECOMMENDED DFT:	1.5 - 2.0 mils DFT
VISCOSITY @ 78°F:	90-95 KU
WEIGHT PER GALLON:	11-11.2 lbs.
FLASH POINT:	102° F
VOC:	<150 G/L

SURFACE PREPARATION:

Proper surface preparation is the most important variable in determining the service life of a coating. For best results, all surfaces must be clean, dry and free from wax, oil, grease, dirt, mildew, and any other contaminants. For New Wood Surfaces, it is necessary to first apply a prime coat of appropriate Tallman's Exterior Primer. Allow primer to dry thoroughly before application of the finish coat. For Previously Painted Surfaces, it is recommended that highly weathered areas be sanded, and spot primed. All loose paint should be removed by chipping, sanding, scraping, grinding or sand blasting. Feather sand rough edges for imperfections.

APPLICATION:

Apply by natural bristle brush, roller or spray. Do Not Thin; use as is from the container. Do not add oils or any other paints to this product. Before and during application, stir the paint thoroughly from the bottom of the can with an upward motion, scraping the bottom to avoid pigment settling.

ENVIRONMENTAL VARIABLES:

Apply only when surface and air temperatures are between 50° and 90°F. Avoid painting on hot days, in direct sunlight or late in the day when dew is likely to form. Cool, wet, humid or over-applied coatings can greatly decrease a thorough cure and interfere with proper film formation.

Dry-Times:

Drying time for this product will be approximately 24 hours to touch and may be recoated after 48 hours under ideal drying conditions.

CLEAN-UP:

Clean up all tools and equipment with Mineral Spirits before paint is allowed to dry. To avoid spontaneous combustion during storage, soak soiled rags and waste immediately after use in a water-filled closed metal container.

1372

**Exterior Oil Barn & Building
Semi-Gloss White Oil**



Product Data Sheet

CAUTIONS:

For additional Product Information or Safety Data Sheets, please call 800-677-2468, 8:00-5:00 CST Mon.-Fri.

Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since Tallman's does not control the application of its products, or the condition of the surfaces to which they are applied, Tallman Ag Specialty's® liability will under no circumstances exceed replacement of the product.