

1522

Exterior Latex Primer

Flat White



Product Data Sheet

PRODUCT DESCRIPTION:

Tallman Ag Specialty Exterior Latex Primer is formulated to meet rigid performance requirements for durability and service. It is custom-built to provide a uniform base on new wood or badly weathered old siding. It is specifically designed to provide easy application, excellent adhesion, and superior resistance to weather. For use under latex finish coats. Tallman Exterior Latex Primer can be tinted with any universal tinting system to match topcoat colors (in pastel or tint base colors).

TYPICAL USES:

Tallman Ag Specialty Exterior Latex Primer can be used on all properly prepared surfaces of wood, siding and trim.

BASES & COLORS:

Flat White

PHYSICAL PROPERTIES:

| | |
|-----------------------------------|----------------------------|
| PRODUCT NUMBER: | 1522 |
| GENERAL TYPE: | Exterior Latex Flat Primer |
| COLOR: | White |
| GLOSS: | 1-10 @ 60° |
| SOLIDS BY WEIGHT: | 44.6% |
| SOLIDS BY VOLUME: | 30.4% |
| THEORETICAL COVERAGE @ 1 MIL DFT: | 487 SF./Gal |
| RECOMMENDED DFT: | 1.5-2.0 mils DFT |
| VISCOSITY @ 78°F: | 90-95 KU |
| WEIGHT PER GALLON: | 10.5- 10.6 lbs. |
| FLASH POINT: | None |
| VOC: | 139 G/L |

SURFACE PREPARATION:

Proper surface preparation is the most important variable in determining the service life of a coating. For best results, all surfaces must be clean, dry and free from wax, oil, grease, dirt, mildew, loose rust and any other contaminants. Glossy surfaces should be lightly sanded. Scrape off all loose cracking, peeling paint and make sure all imperfections are repaired. Powdery or chalky surfaces must be cleaned before paint application.

APPLICATION:

Apply by brush, roller or airless spray. Do not thin except for airless spray application, in which case you may thin with up to 10% clean water, if needed. May be applied to slightly damp surfaces. Do not mix with solvent paints, oils, thinners or turpentine. Before and during application, stir the paint thoroughly from the bottom of the can with an upward motion, scraping the bottom to avoid pigment settling.

ENVIRONMENTAL VARIABLES:

Apply only when surface and air temperatures are between 50° and 90°F. Avoid painting late in the day when dew and condensation are likely to form or when rain is threatening. Avoid painting on hot days in direct sunlight. Cool, wet, humid or over-applied coatings can greatly decrease a thorough cure and interfere with proper film formation. Always allow applied coat to dry before applying subsequent coats.

Dry-Times:

Drying time for this product will be approximately 1 hour to touch and may be recoated after 6 hours under ideal drying conditions.

CLEAN-UP:

Clean up all tools and equipment with warm, soapy water before paint dries.

1522
Exterior Latex Primer
Flat White



Product Data Sheet

CAUTIONS:

For additional Product Information or Safety Data Sheets, please call 800-677-2468, 8:00-5:00 CST Mon.-Fri.

Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since Tallman's does not control the application of its products, or the condition of the surfaces to which they are applied, Tallman Ag Specialty's liability will under no circumstances exceed replacement of the product.