

1525

Barn and Outbuilding Latex Semi-gloss White Finish



Product Data Sheet

PRODUCT DESCRIPTION:

Tallman Ag Specialty Barn and Outbuilding Latex is our finest quality latex custom built for superior performance. Specifically formulated to provide excellent exterior durability, high hiding, and excellent color. It is made to be extremely resistant to cracking, chipping, peeling and blistering. It has excellent hiding that will resist fading for years.

TYPICAL USES:

Tallman Ag Specialty Barn and Outbuilding Latex is designed for use on all properly prepared surfaces of wood, siding, masonry, concrete block, asbestos, shingles and trim. Primer may be necessary to block stains, improve corrosion resistance, enhance adhesion and lower the project cost.

BASES & COLORS:

1525 Barn and Outbuilding Latex, Semi-Gloss White

PHYSICAL PROPERTIES:

PRODUCT NUMBER:	1525
GENERAL TYPE:	Exterior Latex Semi-Gloss
COLOR:	White
GLOSS:	30-50 @ 60°
SOLIDS BY WEIGHT:	43.6%
SOLIDS BY VOLUME:	31.9%
THEORETICAL COVERAGE @ 1 MIL DFT:	511 SF. /Gal
RECOMMENDED DFT:	2.0 – 4 mils DFT
VISCOSITY @ 78°F:	90-95 KU
WEIGHT PER GALLON:	10.2- 10.3 lbs.
FLASH POINT:	None
VOC:	113.0 G/L

SURFACE PREPARATION:

Proper surface preparation is the most important variable in determining the service life of a coating. For best results, all surfaces must be clean, dry and free from wax, oil, grease, dirt, mildew, loose rust and any other contaminants. **NEW WOOD SURFACES:** Prime with at least one coat of exterior latex or oil primer. **PREVIOUSLY PAINTED SURFACES:** Scrape off all loose cracking, peeling paint and make sure all imperfections are repaired. **MASONRY:** Must cure for at least 60 days and be clean and free of dirt and sand. Old masonry must be thoroughly cleaned of peeling paint, loose sand, efflorescence and mildew. Apply 2 coats of paint. **METAL:** Prime bare metal with Metal Primer, 2 coats recommended, and allow ample drying time before recoating. Powdery or chalky surfaces must be cleaned before paint application. Glossy surfaces should be lightly sanded before painting.

APPLICATION:

Apply by nylon or polyester brush, roller or AIRLESS spray. Do not thin except for airless spray application, in which case you may thin with up to 10% clean water, if needed. May be applied to slightly damp surfaces. Do not mix with solvent paints, oils, thinners or turpentine. Before and during application, stir the paint thoroughly from the bottom of the can with an upward motion, scraping the bottom to avoid pigment settling.

ENVIRONMENTAL VARIABLES:

Apply only when surface and air temperatures are between 50° and 90°F. Avoid painting late in the day when dew and condensation are likely to form or when rain is threatening. Avoid painting on hot days in direct sunlight. Cool, wet, humid or over-applied coatings can greatly decrease a thorough cure and interfere with proper film formation. Always allow applied coat to dry before applying subsequent coats.

Dry-Times:

Drying time for this product will be approximately 1 hour to touch and may be recoated after 6 hours under ideal drying conditions.

CLEAN-UP:

Clean up all tools and equipment with warm, soapy water before paint is allowed to dry.

1525

**Barn and Outbuilding Latex
Semi-gloss White Finish**



Product Data Sheet

CAUTIONS:

For additional Product Information or Safety Data Sheets, please call 800-677-2468, 8:00-5:00 CST Mon.-Fri.

Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since Tallman's does not control the application of its products, or the condition of the surfaces to which they are applied, Tallman Ag Specialty's liability will under no circumstances exceed replacement of the product.